



## ROMAN STUCCO FOR MICROMOSAIC 20 GR

Roman stucco for micromosaic made with linseed oil.

- This stucco has been aged for 12 months and is ready to be ground, mixed with linseed oil, and used with our glass threads (code #F006619 and #F006618).
- For grinding, it is recommended to break it into smaller pieces with a hammer or nippers and then grind it with a mortar to obtain a very fine powder.
- Mix the powder with linseed oil to obtain the desired consistency.
- The slow drying of this putty will allow you to work calmly on your micromosaic for several days.
- It is recommended to wait at least 3 weeks once the piece is finished before handling it or performing further work.
- 20 grams of stucco allow you to create between 15 and 20 micromosaics of approximately 2.5 / 3 cm in diameter.

### SPECIFICHE

SKU	Packaging
55869	20 GR